

SuperPolart® triple recubrimiento brillante.

ESPECIFICACIONES

GRAMAJE	g/m ²	90	100	135	150	200	250	300
Tol. ±		3	4	4	5	6	8	12
CALIBRE	µm	68	75	97	108	150	195	242
Tol. ±		3	4	5	5	8	8	13
BLANCURA	%	93.5	93.5	94	94	94	94	94
Tol. ±		1.5	1.5	1.5	1.5	1.5	1.5	1.5
OPACIDAD	%	90	92	96	-	-	-	-
Tol. ±		2	2	2	-	-	-	-
BRILLANTEZ	%	74	74	79	79	79	78	78
Tol. ±		4	4	4	4	4	4	4
TINTA								
a*		1.60	1.60	1.60	1.60	1.60	1.60	1.52
b*		-7.5	-7.5	-7.5	-7.5	-7.5	-7.5	-6.72
Tol. ±		0.75	0.75	0.75	0.75	0.75	0.75	0.75
L*		94.26	94.26	94.26	94.26	94.26	94.26	93.97
Tol. ±		1	1	1	1	1	1	1