

SuperPolart® triple recubrimiento semimate.

ESPECIFICACIONES

GRAMAJE	g/m ²	90	100	135	150	200	250
Tol. ±		3	4	4	5	8	8
CALIBRE	μm	76	84	109	122	172	223
Tol. ±		4	4	5	6	9	12
BLANCURA	%	97	97	97	97	97	97
Tol. ±		1.5	1.5	1.5	1.5	1.5	1.5
OPACIDAD	%	91	93	96	-	-	-
Tol. ±		2	2	2	-	-	-
LISURA	ε	450	450	450	400	250	250
Tol. ±		130	130	130	120	80	80
COLOR							
a*		1.90	1.90	1.90	1.90	1.90	1.90
b*		-8.0	-8.0	-8.0	-8.0	-8.0	-8.0
Tol. ±		0.75	0.75	0.75	0.75	0.75	0.75
L*		94.85	94.85	94.85	94.85	94.85	94.85
Tol.±		1	1	1	1	1	1